


Zapp is certified to ISO 9001



Grade Zapp® 1.4034 YK

Zapp® 1.4034 YK is a martensitic stainless steel with 13 % chromium content. In conducting an appropriate heat treatment a maximum hardness of 57 HRC* can be achieved. The best corrosion resistance to moderate aggressive, non-chloric media is achieved in the hardened and high gloss polished condition with a metallic bright surface.

Typical Fields of Application

- Surgical Instruments
- Cutting Tools, e. g. Scissors, Doctor blades
- Bone Cutters, Burrs
- Medical Screwdrivers
- Dental Instruments, e.g. Cutters, Burrs and Curettes

Weldability

Usually, Zapp® 1.4034 YK is not used for welding. Limited weldability with arc welding. Parts should be heat treated after welding.

Polishability

Zapp® 1.4034 YK is high gloss polishable.

Magnetism

Zapp® 1.4034 YK is magnetizable.

Cold Working

Zapp® 1.4034 YK should be cold worked in the soft-annealed condition.

Machining

Best results can be achieved in the soft-annealed and redrawn condition.

* Maximum hardness achievable under ideal hardening conditions

Corresponding Standards

- 1.4034 (X46Cr13) acc. to DIN EN 10088-3
- 1.4034 (X46Cr13) acc. to NF S 94-090
- AISI 420C (UNS S42000) acc. to ASTM F899
- Reference letter D acc. to EN ISO 7153-1

Typical Chemical Composition *

C	Si	Mn	Cr	P	S
0.46	0.50	0.50	13.50	0.02	0.015

* Average in mass-%

Mechanical Properties (Soft-Annealed)

Tensile Strength TS	[ksi]	87.0 – 108.8
Yield Strength	[ksi]	min. 50.8
Elongation A5	[%]	min. 20
Hardness HB		max. 245
Structure		Ferrite + Carbides

Mechanical Properties (Cold-Worked)

Tensile Strength TS	[ksi]	116.0 – 159.5
Yield Strength YS	[ksi]	max. 116.0

Physical Properties

Modulus of Elasticity E 70 °F	[ksi]	31,183
Specific Density	[lb/in³]	0.28
Thermal Conductivity 70 °F	[Btu in/hr ft² °F]	208.0
Coefficient of Thermal Expansion	[µin/in °F]	
70 - 210 °F		5.8
70 - 390 °F		6.1
70 - 570 °F		6.4
70 - 750 °F		6.7
70 - 930 °F		6.7
Specific Heat 70 °F	[Btu/lb °F]	0.11
Electric Resistivity 70 °F	[Ω circular-mil/ft]	330.8

Hot Working

Forging temperature is 1,470 – 2,010 °F:
heat slowly up to approx. 1,470 °F.
Afterwards heat up rapidly to the required forging
temperature. Cool slowly after forging (e.g. in
furnace).

Heat Treatment

Soft-Annealing

Temperature: 1,380 – 1,560 °F
Holding time: 2 - 6 h
Cooling: furnace, air


Hardening

Temperature: 1,830 – 1,920 °F
Holding time: approx. 0,5 h (depends on
cross-section)
Cooling: oil
Hardened structure: martensite + carbides

Tempering


Temperature: see tempering chart
Holding time: approx. 1 h (depends on cross-section)
Cooling: oil, air
Due to the 855 °F embrittlement tempering in this
range should be avoided.

Tempering Chart
Hardness HRC



According to the required hardness and the actual
dimension the hardening and tempering temperature
have to be selected from the respective ranges.

Corrosion Resistance



MEDICAL ALLOYS

Zapp Precision Metals GmbH
Letmather Straße 69
58239 Schwerte
medicalalloys@zapp.com
www.zapp.com

Further information regarding our products and locations are
available in our image brochure and under www.zapp.com

The illustrations, drawings, dimensional and weight data and other
information included in this data sheet are intended only for the
purposes of describing our products and represent non-binding
average values. They do not constitute quality data, nor can they be
used as the basis for any guarantee of quality or durability. The
applications presented serve only as illustrations and can be
construed neither as quality data nor as a guarantee in relation to
the suitability of the material. This cannot substitute for
comprehensive consultation on the selection of our products and on
their use in a specific application.
The brochure is not subject to change control.
Last revision: June 2026