


Zapp is certified to ISO 9001



Zapp® 9.9135 HN

Zapp® 9.9135 HN is a cobalt-chromium-molybdenum alloy. It is characterized by high biocompatibility and high corrosion resistance. Due to its low nickel content, the Zapp® 9.9135 HN is particularly suitable for allergy sufferers.

The material has the highest wear resistance and hardness. The vacuum melting results in an outstanding degree of slag purity.

Typical Applications

- Osteosynthesis
- Spinal uses
- Dental applications

Polishability

Zapp® 9.9135 HN is high gloss polishable.

Magnetism

Zapp® 9.9135 HN is not magnetizable.

Corrosion Resistance

The high molybdenum content leads to a fast regeneration of the passive layer on the steel surface. Therefore, the material has a high corrosion resistance, e.g. against seawater.

Cold Working

Cold working of Zapp® 9.9135 HN is not recommended.

Wear Resistance

Zapp® 9.9135 HN has a high wear resistance. This property mostly remains at high temperatures.

Machining

Due to the high chromium content, the machining of the Zapp® 9.9135 HN is demanding. Therefore, the tools and the production parameters must be adapted accordingly.

Corresponding Standards

- According to DIN EN ISO 5832-12
- According to ASTM F1537

Typical Chemical Composition [Mass-%]

	C	Si	Mn	Cr	Mo	Fe
Min.	-	-	-	26.0	5.0	-
Max.	0.14	1.0	1.0	30.0	7.0	0.75
	Co	N	Ni	P		
Min.	-	-	-	-		
Max.	bal.	0.25	0.1	0.015		

Mechanical Properties

Condition	Tensile strength Rm [ksi]	Yield strength Rp _{0.2} [ksi]	Elongation A [%]	Hardness [HRC]
Annealed	> 130	> 75	> 20	~ 25
Hot-worked	> 145	> 100	> 12	~ 28
Warm worked	> 170	> 120	> 12	~ 35
Warm worked premium	> 170	> 120	> 25	~ 35

Physical Properties

Modulus of Elasticity E at 68 °F	[ksi]	34,954
Specific gravity ρ	[lb/ in³]	0.3
Thermal Conductivity λ at 68 °F	[Btu in/hr ft² °F]	90.0
Coefficient of Thermal Expansion α	[μ in/in °F]	
68 – 212 °C		7.3
68 – 392 °C		7.4
68 – 572 °C		7.5
68 – 752 °C		7.7
68 – 932 °C		7.8
Specific Heat c at 68 °F	[Btu/lb °F]	107

Heat Treatment

Solution Annealing:

Temperature: 1,967 – 2,102 °F

Holding Time: 30 Min.

Cooling: Air

MEDICAL ALLOYS

Zapp Precision Metals GmbH

Letmather Straße 69

58239 Schwerte

medicalalloys@zapp.com

www.zapp.com

Further information regarding our products and locations are available in our image brochure and under www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.
Last revision: June 2026